



**اطلس تايل**  
**ATLAS TILE**

**تعليمات بازل الاستعمال**  
يجب ان يكون السطح المراد تغطيته نظيفاً جافاً خالياً من الزيوت والدهايات والمواد الحامضية او القلوية او غيرها من المواد الضارة بالادوية اللاصقة. يجب ان يكون السطح المراد تغطيته خالياً من الرطوبة او الماء او الثلج او الجليد او غيرها من المواد الضارة بالادوية اللاصقة. يجب ان يكون السطح المراد تغطيته خالياً من الغبار او الرمل او غيرها من المواد الضارة بالادوية اللاصقة.

**تعليمات الاستعمال**  
يجب تطبيق الادوية اللاصقة بطبق واحد على السطح المراد تغطيته. يجب ان يكون السطح المراد تغطيته خالياً من الرطوبة او الماء او الثلج او الجليد او غيرها من المواد الضارة بالادوية اللاصقة. يجب ان يكون السطح المراد تغطيته خالياً من الغبار او الرمل او غيرها من المواد الضارة بالادوية اللاصقة.

**الاستخدامات**  
1- لاصق بلاستيكي للسيراميك والبلاط والرخام.  
2- لاصق بلاستيكي للسيراميك والبلاط والرخام في الحمامات والمطابخ.  
3- لاصق بلاستيكي للسيراميك والبلاط والرخام في الحمامات والمطابخ.

**التغطية**  
1- في مساحة بلاط السيراميك 2 كجم من الادوية اللاصقة.  
2- في مساحة بلاط الرخام 2 كجم من الادوية اللاصقة.

**السمية والسلامة**  
لا تحتوي الادوية اللاصقة على مواد سامة او ضارة بالصحة. يجب تجنب الاتصال بالادوية اللاصقة في العينين او الفم او على الجلد.

**DIRECTIONS BEFORE USE**  
• The surface to be tiled should be clean, dry and free from oil.  
• In the conditions used for these tiles use a trowel spreader.  
• For porous substrates (ie gypsum board or porous brick, primer surface with a suitable primer (ie SALU BOND).

**DIRECTIONS FOR USE**  
Mix ATLAS TILE to a paste of the ratio of 2 : 1  
Leave to stand for 5 - 10 minutes then use.

**APPLICATION**  
1) Apply to a depth of 2 - 8 mm depending on tile size.  
2) Ensure that at least 70% of each tile is in contact with adhesive.  
3) Leave for at least 24 hours before grouting.

**COVERAGE**  
1) 1kg of tile fixing approximately 2 Kg. Per m<sup>2</sup>.  
2) 2kg of tile fixing approximately 4 Kg. Per m<sup>2</sup>.

**HEALTH AND SAFETY**  
ATLAS TILE is not a hazardous material. Still take care to avoid dust inhalation and eye and skin contact.

**20 KILOS WHITE ٢٠ كيلو ابيض**

# ATLAS TILE ADHESIVE

ATLAS TILE Waterproof Adhesive is a high performance adhesive that is specifically designed for a wide range of heavy duty tile fixing.

## COMPOSITION

The active ingredients include Portland cement, filler, fine graded sand, chemical additives and high organic polymer content.

## PREPERATIONS

Ensure that the surface to be covered by mineral coating. Surface should be clean from dust, flakes, loose particles, mould oil, grease and free of any foreign matter. Spray some potable water before to neutralize the background. Application of adhesive start after complete evaporation of sprayed water.

## MIXING

ATLAS TILE WATER PROOF ADHESIVE should be mixed thoroughly with approximately 25% water according to product's weight. That is 5 liter water for 20 kg bag. Electrical hand mixer is recommended for mixing of adhesive in a clean container. After mixing should be allowed to stand for 5 – 10 minutes for proper dissolving of all additives. After maturing thick paste, stir again without addition of water. Mixed mortar should be used within 45 minutes.

## APPLICATION

- » Apply The mixed mortar on prepared background with comb trowel at thickness of 3-5mm
- » Fix the tile on the mortar applied on the wall or floor. Drag left to right and down to up with pressing properly then keep on position
- » Use rubber mallet to fix on proper level and spacing
- » Ensure that at least 75% of each is in contact with adhesive
- » Do not spread the mixed mortar more than one square meter area at a time
- » Leave for at least 24 hours before grouting
- » To ensure even spacing, tile spacers of the required thickness

## PACKAGING

ATLAS TILE WATER PROOF ADHESIVE is packed in 20kg plastic Bags, or it can be custom packaged to suit specific job requirements.

## STORAGE

Material should be stored in a dry covered area protected from elements. Unopened bags have a shelf of 12 month.

## SAFETY PROCEDURES

Wear safety such as rubber gloves, dust mask and safety glasses used to handle conventional cement based products should be worn. In case of contact with eyes, rinse with plenty of water and seek medical advice accordingly. MSDS are available upon request.

## TECHNICAL ASSISTANCE

For advice on how to use SALI TILE GROUT product, consult your nearest SALINA technical office.

### Dubai

United Arab Emirates  
Tel: +971 4 3232935  
Fax: +971 4 3232936  
P.O.Box 32143

### Riyadh

Saudi Arabia  
Tel: +966 1 4984266  
Fax: +9661 4984277  
P.O.Box 5590 ZIP 14432

### Sharjah

United Arab Emirates  
Tel: +971 6 7434488  
Fax: +971 6 7434484  
P.O.Box 23872

### Cairo

Egypt  
Tel: +20 55 2642048  
Fax: +20 55 2574776  
P.O.Box 911 Heliopoes

### Abu Dhabi

United Arab Emirates  
Tel: +971 2 6782206  
Fax: +971 2 6783058  
P.O.Box 70148

### Mississauga

Ontario, Canada  
Tel: +1 647 984 6479  
Fax: +1 905 232 4720  
P.O.Box 958 summerbreeze  
crt. LV 1C9

## COLORS

- » White
- » Gray

## FEATURES

- » Excellent adhesion.
- » Resistance to water, chemicals, and oils.
- » Improved workability.
- » Economical contract packing.
- » High compressive strength
- » Increased bonding strength.
- » Long open time
- » Slip resistant.

## USES

- » Fixing of ceramic floors and wall tiles, swimming pool tiles and decorative stone cladding or marble.

## GROUTING

Attention is mandatory with the grouting process to ensure satisfactory results. Grouting should not be applied until at least 2 days have passed since the completion of tiling.

## TECHNICAL DATA

<b>Physical State</b>	Solid Powder
<b>Binder</b>	Portland Cement
<b>Color</b>	Grey & White
<b>Granular Size</b>	0 – 0.4 mm
<b>Water Requirement</b>	25 % Approx.*
<b>Yield</b>	670 Lit./ Ton approx.*
<b>Working Time</b>	40 Min.*
<b>Dry Density</b>	1.40 Kg/L*
<b>Compressive strength</b>	20 N/mm <sup>2</sup> @ 28 Days*
<b>Flexural Strength</b>	3 N/mm <sup>2</sup> @28 days*
<b>Bond Standards</b>	1.2 N/mm <sup>2</sup> @14Days
<b>Curing</b>	2 days @ 3 times/day
<b>Shelf Life</b>	12 Months from Mfg. Date

\* Test results as per laboratory condition