

# SALINA LIMITED COMPANY



## SALINA STUCCO SS 750

Salina stucco filler is a pre-mixed skim coat plaster for uneven surface application. Provides smooth leveled surface over concrete or plastered surfaces for paint application. Work as water proof coating for internal and external walls.



[www.salinagroup.com](http://www.salinagroup.com)



# SALINA STUCCO

## SS - 750

### DESCRIPTIONS

Salina stucco filler is a pre-mixed skim coat plaster for uneven surface application. Provides smooth leveled surface over concrete or plastered surfaces for paint application. Work as water proof coating for internal and external walls.

### COMPOSITION

Consisting Portland cement, high quality fillers and chemical improving agents, those ensuring good workability and bond strength.

### FEATURES& ADVANTAGES

- Easy application and Good workability.
- Extra smooth finishing.
- Water Resistant.
- Better bonding with variety of substrates.
- Interior or Exterior applications.

### BACKGROUND PREPARATION

Remove all residual mould oil, dust, loose particles, flakes and other contaminations from the background to be applied. Spray clean water to the wall for kill the suction. Allow some time for free water to evaporate completely from the surface.

### STORAGE

The material should be stored in a clean and dry environment protected from direct sunlight and extreme heat or cold. Unopened bags have a shelf life of 12 months.

### MIXING

Salina stucco filler should be mixed in clean container by using electrical hand stirrer to obtain perfect and homogenous mix. Only potable water should be added to achieve a creamy and workable thick plaster, approx 7-8 liters of water is required for each 20kg bag. Leave the mix for 5 min for proper dissolving of additives. Mix again prior to application without addition of water. Harden or partially set material should not be used for mixing and mixed material should be used within hour.

### COVERAGE

Approximately 10 m<sup>2</sup> per 20 kg bag @ 1mm thickness.\*\*

### APPLICATION

Salina stucco filler can be applied on prepared background by putty knife or spatula. Apply the filler as thin even layers. If the area under repair requires a thick coat then apply several thin layers allowing each layer to dry before adding the next. Lightly sand paper over the dry final surface before painting preferably within 24 hours of application. Finished stucco should be cure with potable water.

### HEALTH AND SAFETY

Use under well ventilated conditions with safety essentials like mask, gloves and Safety glasses. Do not breathe or inhale mist. Avoid skin contact; spillage on the skin should be immediately removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention must be sought immediately.

### TECHNICAL ASSISTANCE

Technical support for product application, consult your nearest SALINA technical office or visit our website.



## Technical Data

Salina Stucco SS - 750

Physical State	Powder mix	Dry Density	1.3 Kg/ liter*
Binder	Portland Cement	Coverage	10 m <sup>2</sup> Per 20 Kg Bag @ 1 mm Thickness **
Color	White	Compressive Strength	10 N/mm <sup>2</sup> @ 28 Days*
Granular Size	0 – 0.1 mm	Flexural Strength	3 N/mm <sup>2</sup> @ 28 Days*
Water requirement	35 %*	Curing	Minimum 2 Days, 2 times/day
Packaging	10 Kg & 20 Kg Bag	Shelf life	12 Months from the date of Mfg.
Working Time	30 min Approximately*		

\* Test results as per laboratory conditions.

\*\* Coverage of product may vary with respect to wall perfection, thickness, wastages and applicator skill.

Dubai - U.A.E : Tel: +971 4 3232935 | Fax: +971 4 3232936 | P.O.Box: 32143  
Sharjah - U.A.E : Tel: +971 6 7434488 | Fax: +971 6 7434484 | P.O.Box: 23872  
Doha - Qatar : Tel: +974 4 4604075 | Fax: +974 4 4604497 | P.O.Box: 40411  
Riyadh - KSA : Tel: +966 1 4984266 | Fax: +966 1 4984277 | P.O.Box: 5590 ZIP 11432  
Cairo - Egypt : Tel: +205 5 2572094 | Fax: +205 5 2574776 | P.O.Box: 911 Heliopoes  
Ontario - Canada : Tel: (+164) 79846479 | Fax: (+190)52324720 | P.O.Box: 958 Summerbreeze Crt L5V 1C9  
info@Salinagroup.com - www.SalinaGroup.com

